CLAY FACE BRICK

Woodbridge
Handmade Range

76
230
110

| Product Information	Solid
Work Size (mm)	230 x 110 x 76
Dimensional Category	DW0
Approximate Unit Weight (kg)	2.9
Approximate No. per m²	48.5
No. Per Pack	264
Pack Weight (kg)[1]	789
Characteristic Unconfined Compressive Strength (MPa) $f'uc$	>6
Cold Water Absorption (%)	<20
Coefficient of Expansion (mm/m)	<0.8
Durability Class	Exposure Grade - Marine
Initial Rate of Absorption (kg/m²/min)	<2.8
Potential to Effloresce	Nil
Liability to Lime Pitting	Nil-Slight
Core Percentage	-
Solar Absorption Rating	Light to Medium
Fire Resistance – Insulation (minutes)	90

This technical information represents average properties obtained from production runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic condition. Colours are indicative only. Information subject to change without notice.

[1]Includes +3% moisture

Handmade Range – Clay Face Bricks

Caversham	Helena Vale	Sandalford	Woodbridge

Note: If you require specific or improved product specificiations please contact your Sales Representative.