



A BORAL COMPANY

CLAY FACE BRICK

Amber Pearl Pearl Range






Product Information	Cored	Solid
Work Size (mm)	230 x 110 x 76	230 x 110 x 76
Dimensional Category	DW1	DW1
Approximate Unit Weight (kg)	2.9	3.9
Approximate No. per m ²	48.5	48.5
No. Per Pack	264	264
Pack Weight (kg) ¹	789	1060
Characteristic Unconfined Compressive Strength (MPa) f'uc	>15	>15
Cold Water Absorption (%)	<10	<10
Coefficient of Expansion (mm/m)	<0.8	<0.8
Durability Class	General Purpose	General Purpose
Initial Rate of Absorption (kg/m²/min)	<1.0	<1.0
Potential to Effloresce	Nil-Slight	Nil-Slight
Liability to Lime Pitting	Nil	Nil
Core Percentage	<30	-
Solar Absorption Rating	Dark	Dark
Fire Resistance – Insulation (minutes)	90	90

This technical information represents average properties obtained from production runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic condition. Colours are indicative only. Information subject to change without notice.

¹Includes +3% moisture

Pearl Range - Clay Face Bricks












Note: If you require specific or improved product specificiations please contact your Sales Representative.



A BORAL COMPANY

CLAY FACE BRICK

Black Pearl Pearl Range






Product Information	Cored	Solid
Work Size (mm)	230 x 110 x 76	230 x 110 x 76
Dimensional Category	DW1	DW1
Approximate Unit Weight (kg)	2.8	3.9
Approximate No. per m ²	48.5	48.5
No. Per Pack	264	264
Pack Weight (kg) ¹	761	1060
Characteristic Unconfined Compressive Strength (MPa) f 'uc	>12	>12
Cold Water Absorption (%)	<10	<10
Coefficient of Expansion (mm/m)	<0.8	<0.8
Durability Class	General Purpose	General Purpose
Initial Rate of Absorption (kg/m²/min)	<1.2	<1.2
Potential to Effloresce	Nil-Slight	Nil-Slight
Liability to Lime Pitting	Nil	Nil
Core Percentage	<30	-
Solar Absorption Rating	Dark	Dark
Fire Resistance – Insulation (minutes)	90	90

This technical information represents average properties obtained from production runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic condition. Colours are indicative only. Information subject to change without notice.

¹Includes +3% moisture

Pearl Range - Clay Face Bricks











,


Note: If you require specific or improved product specificiations please contact your Sales Representative.




A BORAL COMPANY

CLAY FACE BRICK

Copper Pearl Pearl Range






Product Information	Cored	Solid
Work Size (mm)	230 x 110 x 76	230 x 110 x 76
Dimensional Category	DW1	DW1
Approximate Unit Weight (kg)	2.8	3.9
Approximate No. per m ²	48.5	48.5
No. Per Pack	264	264
Pack Weight (kg) ¹	761	1060
Characteristic Unconfined Compressive Strength (MPa) f'uc	>15	>18
Cold Water Absorption (%)	<10	<10
Coefficient of Expansion (mm/m)	<0.8	<0.8
Durability Class	General Purpose	General Purpose
Initial Rate of Absorption (kg/m²/min)	<0.8	<1.4
Potential to Effloresce	Nil-Slight	Nil-Slight
Liability to Lime Pitting	Nil	Nil
Core Percentage	<30	-
Solar Absorption Rating	Dark	Dark
Fire Resistance – Insulation (minutes)	90	90

This technical information represents average properties obtained from production runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic condition. Colours are indicative only. Information subject to change without notice.

¹Includes +3% moisture

Pearl Range - Clay Face Bricks





Note: If you require specific or improved product specificiations please contact your Sales Representative.










A BORAL COMPANY

CLAY FACE BRICK

Grey Pearl Pearl Range





Product Information	Cored	Solid
Work Size (mm)	230 x 110 x 76	230 x 110 x 76
Dimensional Category	DW1	DW1
Approximate Unit Weight (kg)	2.7	3.9
Approximate No. per m ²	48.5	48.5
No. Per Pack	264	264
Pack Weight (kg) ¹	734	1060
Characteristic Unconfined Compressive Strength (MPa) f'uc	>12	>18
Cold Water Absorption (%)	<10	<10
Coefficient of Expansion (mm/m)	<0.8	<0.8
Durability Class	Exposure Grade	Exposure Grade
Initial Rate of Absorption (kg/m²/min)	<0.4	<1.2
Potential to Effloresce	Nil-Slight	Nil-Slight
Liability to Lime Pitting	Nil	Nil
Core Percentage	<30	-
Solar Absorption Rating	Medium to Dark	Medium to Dark
Fire Resistance – Insulation (minutes)	90	90

This technical information represents average properties obtained from production runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic condition. Colours are indicative only. Information subject to change without notice.

¹Includes +3% moisture

Pearl Range - Clay Face Bricks












Note: If you require specific or improved product specificiations please contact your Sales Representative.



A BORAL COMPANY

CLAY FACE BRICK

Ivory Pearl Pearl Range






Product Information	Cored	Solid
Work Size (mm)	230 x 110 x 76	230 x 110 x 76
Dimensional Category	DW1	DW1
Approximate Unit Weight (kg)	2.7	3.7
Approximate No. per m ²	48.5	48.5
No. Per Pack	264	264
Pack Weight (kg) ¹	734	1006
Characteristic Unconfined Compressive Strength (MPa) f'uc	>12	>12
Cold Water Absorption (%)	<10	<10
Coefficient of Expansion (mm/m)	<0.8	<0.8
Durability Class	General Purpose	General Purpose
Initial Rate of Absorption (kg/m²/min)	<1.2	<1.5
Potential to Effloresce	Nil-Slight	Nil-Slight
Liability to Lime Pitting	Nil	Nil
Core Percentage	<30	-
Solar Absorption Rating	Light	Light
Fire Resistance – Insulation (minutes)	90	90

This technical information represents average properties obtained from production runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic condition. Colours are indicative only. Information subject to change without notice.

¹Includes +3% moisture

Pearl Range - Clay Face Bricks





Note: If you require specific or improved product specificiations please contact your Sales Representative.





