


CLAY PAVER

Golden Dune Coach Road Pave Coach



| Product Information | |
|---------------------------------------|-----------------|
| Work Size (mm) | 230 x 114 x 76 |
| Dimensional Category | DPA2 |
| Approximate Dry Unit Weight (kg) | 3.7 |
| Approximate No. per m ² | 37.2 |
| No. Per Pack | 264 |
| Nominal Pack Weight (kg) ¹ | 1006 |
| Breaking Load (kN) | >10 |
| Mean Abrasion Index (V _a) | <12 |
| Slip Resistance Category | P5 |
| Cold Water Absorption (%) | <12 |
| Coefficient of Expansion (mm/m) | <1.0 |
| Durability Class | General Purpose |
| Potential to Effloresce | Nil to Slight |
| Liability to Lime Pitting | Nil to Slight |
| Solar Absorption Rating | Light |

This technical information represents average properties obtained from production runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

¹ Includes +3% for moisture

Road Pave Coach Clay Paver Range



Golden Dune Coach



Grey Coach



Red Coach



Sentosa Coach



Terracotta Coach




Traditional Coach

Note: If you require specific or improved product specifications please contact your Sales Representative

DISCLAIMER. The information presented herein is supplied in good faith and to the best of our knowledge was correct at the time of preparation. No responsibility can be accepted by Midland Brick Company Pty Ltd, its staff or its agents for any errors or omissions. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, no responsibility can be accepted by Midland Brick Company Pty Ltd, its staff or its agents for any loss or damage caused by any person acting or refraining from action as a result of this information.

CLAY PAVER

Grey Coach Road Pave Coach



| Product Information | |
|---------------------------------------|-----------------|
| Work Size (mm) | 230 x 114 x 76 |
| Dimensional Category | DPA2 |
| Approximate Dry Unit Weight (kg) | 4.0 |
| Approximate No. per m ² | 37.2 |
| No. Per Pack | 264 |
| Nominal Pack Weight (kg) ¹ | 1088 |
| Breaking Load (kN) | >10 |
| Mean Abrasion Index (V _a) | <7 |
| Slip Resistance Category | P5 |
| Cold Water Absorption (%) | <12 |
| Coefficient of Expansion (mm/m) | <1.0 |
| Durability Class | General Purpose |
| Potential to Effloresce | Nil to Slight |
| Liability to Lime Pitting | Nil to Slight |
| Solar Absorption Rating | Medium |

This technical information represents average properties obtained from production runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

¹ Includes +3% for moisture

Road Pave Coach Clay Paver Range



Golden Dune Coach



Grey Coach



Red Coach



Sentosa Coach



Terracotta Coach




Traditional Coach

Note: If you require specific or improved product specifications please contact your Sales Representative

DISCLAIMER. The information presented herein is supplied in good faith and to the best of our knowledge was correct at the time of preparation. No responsibility can be accepted by Midland Brick Company Pty Ltd, its staff or its agents for any errors or omissions. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, no responsibility can be accepted by Midland Brick Company Pty Ltd, its staff or its agents for any loss or damage caused by any person acting or refraining from action as a result of this information.

CLAY PAVER

Red Coach Road Pave Coach



| Product Information | |
|---------------------------------------|-----------------|
| Work Size (mm) | 230 x 114 x 76 |
| Dimensional Category | DPA2 |
| Approximate Dry Unit Weight (kg) | 4.2 |
| Approximate No. per m ² | 37.2 |
| No. Per Pack | 264 |
| Nominal Pack Weight (kg) ¹ | 1142 |
| Breaking Load (kN) | >10 |
| Mean Abrasion Index (V _a) | <7 |
| Slip Resistance Category | P5 |
| Cold Water Absorption (%) | <10 |
| Coefficient of Expansion (mm/m) | <1.0 |
| Durability Class | General Purpose |
| Potential to Effloresce | Nil to Slight |
| Liability to Lime Pitting | Nil to Slight |
| Solar Absorption Rating | Dark |

This technical information represents average properties obtained from production runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

¹ Includes +3% for moisture

Road Pave Coach Clay Paver Range



Golden Dune Coach



Grey Coach



Red Coach



Sentosa Coach



Terracotta Coach




Traditional Coach

Note: If you require specific or improved product specifications please contact your Sales Representative

DISCLAIMER. The information presented herein is supplied in good faith and to the best of our knowledge was correct at the time of preparation. No responsibility can be accepted by Midland Brick Company Pty Ltd, its staff or its agents for any errors or omissions. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, no responsibility can be accepted by Midland Brick Company Pty Ltd, its staff or its agents for any loss or damage caused by any person acting or refraining from action as a result of this information.

CLAY PAVER

Sentosa Coach Road Pave Coach



| Product Information | |
|---------------------------------------|-----------------|
| Work Size (mm) | 230 x 114 x 76 |
| Dimensional Category | DPA2 |
| Approximate Dry Unit Weight (kg) | 4.2 |
| Approximate No. per m ² | 37.2 |
| No. Per Pack | 264 |
| Nominal Pack Weight (kg) ¹ | 1142 |
| Breaking Load (kN) | >10 |
| Mean Abrasion Index (V _a) | <7 |
| Slip Resistance Category | P5 |
| Cold Water Absorption (%) | <10 |
| Coefficient of Expansion (mm/m) | <1.0 |
| Durability Class | General Purpose |
| Potential to Effloresce | Nil to Slight |
| Liability to Lime Pitting | Nil to Slight |
| Solar Absorption Rating | Dark |

This technical information represents average properties obtained from production runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

¹ Includes +3% for moisture

Road Pave Coach Clay Paver Range



Golden Dune Coach



Grey Coach



Red Coach



Sentosa Coach



Terracotta Coach




Traditional Coach

Note: If you require specific or improved product specifications please contact your Sales Representative

DISCLAIMER. The information presented herein is supplied in good faith and to the best of our knowledge was correct at the time of preparation. No responsibility can be accepted by Midland Brick Company Pty Ltd, its staff or its agents for any errors or omissions. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, no responsibility can be accepted by Midland Brick Company Pty Ltd, its staff or its agents for any loss or damage caused by any person acting or refraining from action as a result of this information.

CLAY PAVER

Terracotta Coach Road Pave Coach



| Product Information | |
|---------------------------------------|-----------------|
| Work Size (mm) | 230 x 114 x 76 |
| Dimensional Category | DPA2 |
| Approximate Dry Unit Weight (kg) | 3.9 |
| Approximate No. per m ² | 37.2 |
| No. Per Pack | 264 |
| Nominal Pack Weight (kg) ¹ | 1060 |
| Breaking Load (kN) | >10 |
| Mean Abrasion Index (V _a) | <7 |
| Slip Resistance Category | P5 |
| Cold Water Absorption (%) | <10 |
| Coefficient of Expansion (mm/m) | <1.0 |
| Durability Class | General Purpose |
| Potential to Effloresce | Nil to Slight |
| Liability to Lime Pitting | Nil to Slight |
| Solar Absorption Rating | Dark |

This technical information represents average properties obtained from production runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

¹ Includes +3% for moisture

Road Pave Coach Clay Paver Range



Golden Dune Coach



Grey Coach



Red Coach



Sentosa Coach



Terracotta Coach




Traditional Coach

Note: If you require specific or improved product specifications please contact your Sales Representative

DISCLAIMER. The information presented herein is supplied in good faith and to the best of our knowledge was correct at the time of preparation. No responsibility can be accepted by Midland Brick Company Pty Ltd, its staff or its agents for any errors or omissions. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, no responsibility can be accepted by Midland Brick Company Pty Ltd, its staff or its agents for any loss or damage caused by any person acting or refraining from action as a result of this information.

CLAY PAVER

Traditional Coach Road Pave Coach



| Product Information | |
|---------------------------------------|-----------------|
| Work Size (mm) | 230 x 114 x 76 |
| Dimensional Category | DPA2 |
| Approximate Dry Unit Weight (kg) | 4.0 |
| Approximate No. per m ² | 37.2 |
| No. Per Pack | 264 |
| Nominal Pack Weight (kg) ¹ | 1088 |
| Breaking Load (kN) | >10 |
| Mean Abrasion Index (V _a) | <10 |
| Slip Resistance Category | P5 |
| Cold Water Absorption (%) | <10 |
| Coefficient of Expansion (mm/m) | <1.0 |
| Durability Class | General Purpose |
| Potential to Effloresce | Nil to Slight |
| Liability to Lime Pitting | Nil to Slight |
| Solar Absorption Rating | Dark |

This technical information represents average properties obtained from production runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

¹ Includes +3% for moisture

Road Pave Coach Clay Paver Range



Golden Dune Coach



Grey Coach



Red Coach



Sentosa Coach



Terracotta Coach



Traditional Coach

Note: If you require specific or improved product specifications please contact your Sales Representative

DISCLAIMER. The information presented herein is supplied in good faith and to the best of our knowledge was correct at the time of preparation. No responsibility can be accepted by Midland Brick Company Pty Ltd, its staff or its agents for any errors or omissions. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, no responsibility can be accepted by Midland Brick Company Pty Ltd, its staff or its agents for any loss or damage caused by any person acting or refraining from action as a result of this information.