


MASONRY PAVER

# Charcoal Boulevard Classic





Product Information		
Work Size (mm)	400 x 200 x 60	
Dimensional Category	DPA2	
CMAA Shape Category	Type C	
Approximate Dry Unit Weight (kg)	10.3	
Approximate No. per m <sup>2</sup>	12.5	
No. Per Pack	180	
Nominal Pack Weight (kg) <sup>3</sup>	1910	
Breaking Load (kN) <sup>1</sup>	>5	
Mean Abrasion Index (V <sub>a</sub> ) <sup>2</sup>	<12	
Slip Resistance Category	P5	
Cold Water Absorption (%)	<5	
Coefficient of Contraction (mm/m)	<0.8	
Durability Class	General Purpose	
Potential to Effloresce	Slight to Moderate	
Liability to Lime Pitting	Nil	
Solar Absorption Rating	Dark	

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

#### **Boulevard Classic Masonry Paver Range**







Steel Grey

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

<sup>&</sup>lt;sup>1</sup> At 28 days


<sup>&</sup>lt;sup>2</sup> At 90 days

<sup>&</sup>lt;sup>3</sup> Includes +3% for moisture



**MASONRY PAVER** 

## Limestone Boulevard Classic





Product Information		
Work Size (mm)	400 x 200 x 60	
Dimensional Category	DPA2	
CMAA Shape Category	Type C	
Approximate Dry Unit Weight (kg)	10.5	
Approximate No. per m <sup>2</sup>	12.5	
No. Per Pack	180	
Nominal Pack Weight (kg) <sup>3</sup>	1947	
Breaking Load (kN) <sup>1</sup>	>5	
Mean Abrasion Index (V <sub>a</sub> ) <sup>2</sup>	<12	
Slip Resistance Category	P5	
Cold Water Absorption (%)	<5	
Coefficient of Contraction (mm/m)	<0.8	
Durability Class	General Purpose	
Potential to Effloresce	Nil to Slight	
Liability to Lime Pitting	Nil	
Solar Absorption Rating	Light	

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

#### **Boulevard Classic Masonry Paver Range**







Steel Grey

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

<sup>&</sup>lt;sup>1</sup> At 28 days


<sup>&</sup>lt;sup>2</sup> At 90 days

<sup>&</sup>lt;sup>3</sup> Includes +3% for moisture



**MASONRY PAVER** 

## Pewter Boulevard Classic





Product Information		
Work Size (mm)	400 x 200 x 60	
Dimensional Category	DPA2	
CMAA Shape Category	Type C	
Approximate Dry Unit Weight (kg)	10.4	
Approximate No. per m <sup>2</sup>	12.5	
No. Per Pack	180	
Nominal Pack Weight (kg) <sup>3</sup>	1928	
Breaking Load (kN) <sup>1</sup>	>5	
Mean Abrasion Index (V <sub>a</sub> ) <sup>2</sup>	<12	
Slip Resistance Category	P5	
Cold Water Absorption (%)	<5	
Coefficient of Contraction (mm/m)	<0.8	
Durability Class	General Purpose	
Potential to Effloresce	Slight	
Liability to Lime Pitting	Nil	
Solar Absorption Rating	Medium	

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

- <sup>1</sup> At 28 days
- <sup>2</sup> At 90 days
- <sup>3</sup> Includes +3% for moisture

#### **Boulevard Classic Masonry Paver Range**







Steel Grey


Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative



**MASONRY PAVER** 

## Steel Grey Boulevard Classic



Product Information		
Work Size (mm)	400 x 200 x 60	
Dimensional Category	DPA2	
CMAA Shape Category	Type C	
Approximate Dry Unit Weight (kg)	10.4	
Approximate No. per m <sup>2</sup>	12.5	
No. Per Pack	180	
Nominal Pack Weight (kg) <sup>3</sup>	1928	
Breaking Load (kN) <sup>1</sup>	>5	
Mean Abrasion Index (V <sub>a</sub> ) <sup>2</sup>	<12	
Slip Resistance Category	P5	
Cold Water Absorption (%)	<5	
Coefficient of Contraction (mm/m)	<0.8	
Durability Class	General Purpose	
Potential to Effloresce	Slight	
Liability to Lime Pitting	Nil	
Solar Absorption Rating	Medium to Dark	

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

- <sup>1</sup> At 28 days
- <sup>2</sup> At 90 days
- <sup>3</sup> Includes +3% for moisture

#### **Boulevard Classic Masonry Paver Range**







Steel Grey

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative