


MASONRY PAVER

ChalkBoulevard Granite





Product Information		
Work Size (mm)	400 x 200 x 60	
Dimensional Category	DPA2	
CMAA Shape Category	Type C	
Approximate Dry Unit Weight (kg)	10.4	
Approximate No. per m ²	12.5	
No. Per Pack	180	
Nominal Pack Weight (kg) ³	1928	
Breaking Load (kN) ¹	>5	
Mean Abrasion Index (V _a) ²	<7	
Slip Resistance Category	P5	
Cold Water Absorption (%)	<5	
Coefficient of Contraction (mm/m)	<0.8	
Durability Class	General Purpose	
Potential to Effloresce	Nil to Slight	
Liability to Lime Pitting	Nil	
Solar Absorption Rating	Light	

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

3 Includes +3% for moisture

Boulevard Granite Masonry Paver Range







Platinum Titanium

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative


¹ At 28 days

² At 90 days



MASONRY PAVER

GraphiteBoulevard Granite





Product Information	
Work Size (mm)	400 x 200 x 60
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	10.4
Approximate No. per m ²	12.5
No. Per Pack	180
Nominal Pack Weight (kg) ³	1928
Breaking Load (kN) ¹	>5
Mean Abrasion Index (V _a) ²	<7
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

¹ At 28 days

² At 90 days

3 Includes +3% for moisture

Boulevard Granite Masonry Paver Range







Platinum Titanium


Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative



MASONRY PAVER

Platinum Boulevard Granite





Product Information	
Work Size (mm)	400 x 200 x 60
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	10.4
Approximate No. per m ²	12.5
No. Per Pack	180
Nominal Pack Weight (kg) ³	1928
Breaking Load (kN) ¹	>5
Mean Abrasion Index (V _a) ²	<7
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Medium

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.


¹ At 28 days

² At 90 days

3 Includes +3% for moisture

Boulevard Granite Masonry Paver Range







Titanium


Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative



MASONRY PAVER

TitaniumBoulevard Granite



Product Information	
Work Size (mm)	400 x 200 x 60
Dimensional Category	DPA2
CMAA Shape Category	Туре С
Approximate Dry Unit Weight (kg)	10.4
Approximate No. per m ²	12.5
No. Per Pack	180
Nominal Pack Weight (kg) ³	1928
Breaking Load (kN) ¹	>5
Mean Abrasion Index (V _a) ²	<7
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Medium to Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.


¹ At 28 days

² At 90 days

3 Includes +3% for moisture

Boulevard Granite Masonry Paver Range







Titanium

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative