

MASONRY PAVER

Charcoal Coachstone Classic 80mm



Product Information	
Work Size (mm)	230 x 114 x 80
Dimensional Category	DPA2
CMAA Shape Category	Туре С
Approximate Dry Unit Weight (kg)	4.6
Approximate No. per m ²	38.1
No. Per Pack	210
Nominal Pack Weight (kg) ³	995
Breaking Load (kN) ¹	>10
Mean Abrasion Index (V _a) ²	<7
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight to Moderate
Liability to Lime Pitting	Nil
Solar Absorption Rating	Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Coachstone Classic 80mm Masonry Paver Range

Charcoal Donnybrook Heritage Red Limestone Morocco Pewter

Antique Blend

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

Donnybrook Coachstone Classic 80mm



Product Information	
Work Size (mm)	230 x 114 x 80
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	4.5
Approximate No. per m ²	38.1
No. Per Pack	210
Nominal Pack Weight (kg) ³	973
Breaking Load (kN) ¹	>10
Mean Abrasion Index (V _a) ²	<7
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Medium to Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Coachstone Classic 80mm Masonry Paver Range

Charcoal Donnybrook Heritage Red Limestone Morocco Pewter

Antique Blend

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

Heritage Red Coachstone Classic 80mm



Product Information	
Work Size (mm)	230 x 114 x 80
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	4.5
Approximate No. per m ²	38.1
No. Per Pack	210
Nominal Pack Weight (kg) ³	973
Breaking Load (kN) ¹	>10
Mean Abrasion Index (V _a) ²	<10
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Coachstone Classic 80mm Masonry Paver Range

Charcoal Donnybrook Heritage Red Limestone Morocco Pewter

Antique Blend

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

Limestone Coachstone Classic 80mm



Product Information	
Work Size (mm)	230 x 114 x 80
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	4.6
Approximate No. per m ²	38.1
No. Per Pack	210
Nominal Pack Weight (kg) ³	995
Breaking Load (kN) ¹	>12
Mean Abrasion Index (V _a) ²	<7
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Nil to Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Light

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Coachstone Classic 80mm Masonry Paver Range

Charcoal Donnybrook Heritage Red Limestone Morocco Pewter

Antique Blend

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

Morocco Coachstone Classic 80mm



Product Information	
Work Size (mm)	230 x 114 x 80
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	4.5
Approximate No. per m ²	38.1
No. Per Pack	210
Nominal Pack Weight (kg) ³	973
Breaking Load (kN) ¹	>10
Mean Abrasion Index (V _a) ²	<7
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Coachstone Classic 80mm Masonry Paver Range

Charcoal Donnybrook Heritage Red Limestone Morocco Pewter

Antique Blend

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

Pewter Coachstone Classic 80mm



Product Information	
Work Size (mm)	230 x 114 x 80
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	4.5
Approximate No. per m ²	38.1
No. Per Pack	210
Nominal Pack Weight (kg) ³	973
Breaking Load (kN) ¹	>10
Mean Abrasion Index (V _a) ²	<7
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Nil to Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Medium

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Coachstone Classic 80mm Masonry Paver Range

Charcoal Donnybrook Heritage Red Limestone Morocco Pewter

Antique Blend

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

Antique Blend Coachstone Classic 80mm



Product Information	
Work Size (mm)	230 x 114 x 80
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	4.5
Approximate No. per m ²	38.1
No. Per Pack	210
Nominal Pack Weight (kg) ³	973
Breaking Load (kN) ¹	>8
Mean Abrasion Index (V _a) ²	<7
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Coachstone Classic 80mm Masonry Paver Range

Charcoal Donnybrook Heritage Red Limestone Morocco Pewter

Antique Blend

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture