

MASONRY PAVER

Charcoal Intercoach Pave Classic 80mm



Product Information	
Work Size (mm)	225 x 112 x 80
Dimensional Category	DPA2
CMAA Shape Category	Type A
Approximate Dry Unit Weight (kg) ³	4.3
Approximate No. per m ²	39.7
No. Per Pack	270
Nominal Pack Weight (kg)	1196
Breaking Load (kN) ¹	>12
Mean Abrasion Index (V _a) ²	<7
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight to Moderate
Liability to Lime Pitting	Nil
Solar Absorption Rating	Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Intercoach Pave Classic 80mm Masonry Paver Range

Charcoal Heritage Red Morocco Pewter Antique Blend

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

Heritage Red Intercoach Pave Classic 80mm



Product Information	
Work Size (mm)	225 x 112 x 80
Dimensional Category	DPA2
CMAA Shape Category	Type A
Approximate Dry Unit Weight (kg) ³	4.2
Approximate No. per m ²	39.7
No. Per Pack	270
Nominal Pack Weight (kg)	1168
Breaking Load (kN) ¹	>12
Mean Abrasion Index (V _a) ²	<7
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Intercoach Pave Classic 80mm Masonry Paver Range

Charcoal Heritage Red Morocco Pewter Antique Blend

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

Morocco Intercoach Pave Classic 80mm



Product Information	
Work Size (mm)	225 x 112 x 80
Dimensional Category	DPA2
CMAA Shape Category	Type A
Approximate Dry Unit Weight (kg) ³	4.2
Approximate No. per m ²	39.7
No. Per Pack	270
Nominal Pack Weight (kg)	1168
Breaking Load (kN) ¹	>10
Mean Abrasion Index (V _a) ²	<7
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Intercoach Pave Classic 80mm Masonry Paver Range

Charcoal Heritage Red Morocco Pewter Antique Blend

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

Pewter Intercoach Pave Classic 80mm



Product Information	
Work Size (mm)	225 x 112 x 80
Dimensional Category	DPA2
CMAA Shape Category	Type A
Approximate Dry Unit Weight (kg) ³	4.3
Approximate No. per m ²	39.7
No. Per Pack	270
Nominal Pack Weight (kg)	1196
Breaking Load (kN) ¹	>12
Mean Abrasion Index (V _a) ²	<7
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Nil to Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Medium

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Intercoach Pave Classic 80mm Masonry Paver Range

Charcoal Heritage Red Morocco Pewter Antique Blend

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

Antique Blend Intercoach Pave Classic 80mm



Product Information	
Work Size (mm)	225 x 112 x 80
Dimensional Category	DPA2
CMAA Shape Category	Type A
Approximate Dry Unit Weight (kg) ³	4.3
Approximate No. per m ²	39.7
No. Per Pack	270
Nominal Pack Weight (kg)	1196
Breaking Load (kN) ¹	>12
Mean Abrasion Index (V _a) ²	<7
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Intercoach Pave Classic 80mm Masonry Paver Range

Charcoal Heritage Red Morocco Pewter Antique Blend

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture