

MASONRY PAVER

Charcoal

Pavestone Classic 80mm



Product Information	
Work Size (mm)	230 x 114 x 80
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	4.5
Approximate No. per m ²	37.1
No. Per Pack	210
Nominal Pack Weight (kg) ³	973
Breaking Load (kN) ¹	>10
Mean Abrasion Index (V _a) ²	<8
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight to Moderate
Liability to Lime Pitting	Nil
Solar Absorption Rating	Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Pavestone Classic 80mm Masonry Paver Range













Charcoal

Donnybrook

Heritage Red

Limestone

Morocco

Pewter

Autumn Blend

Antique Blend

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

Donnybrook

Pavestone Classic 80mm



Product Information	
Work Size (mm)	230 x 114 x 80
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	4.5
Approximate No. per m ²	37.1
No. Per Pack	210
Nominal Pack Weight (kg) ³	973
Breaking Load (kN) ¹	>12
Mean Abrasion Index (V _a) ²	<10
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Medium to Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Pavestone Classic 80mm Masonry Paver Range







Donnybrook



Heritage Red



Limestone



Morocco



Pewter

Autumn Blend

Antique Blend

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

Heritage Red Pavestone Classic 80mm



Product Information	
Work Size (mm)	230 x 114 x 80
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	4.5
Approximate No. per m ²	37.1
No. Per Pack	210
Nominal Pack Weight (kg) ³	973
Breaking Load (kN) ¹	>10
Mean Abrasion Index (V _a) ²	<10
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Pavestone Classic 80mm Masonry Paver Range













Charcoal

Donnybrook

Heritage Red

Limestone

Morocco

Pewter

Autumn Blend

Antique Blend

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

Limestone

Pavestone Classic 80mm



Product Information	
Work Size (mm)	230 x 114 x 80
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	4.6
Approximate No. per m ²	37.1
No. Per Pack	210
Nominal Pack Weight (kg) ³	995
Breaking Load (kN) ¹	>12
Mean Abrasion Index (V _a) ²	<7
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Nil to Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Light

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Pavestone Classic 80mm Masonry Paver Range













Morocco



Limestone

Pewter

Autumn Blend

Antique Blend

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

Morocco

Pavestone Classic 80mm



Product Information	
Work Size (mm)	230 x 114 x 80
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	4.5
Approximate No. per m ²	37.1
No. Per Pack	210
Nominal Pack Weight (kg) ³	973
Breaking Load (kN) ¹	>10
Mean Abrasion Index (V _a) ²	<7
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Pavestone Classic 80mm Masonry Paver Range













Charcoal

Donnybrook

Heritage Red

Limestone

Morocco

Pewter

Autumn Blend

Antique Blend

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture



A BORAL COMPANY

MASONRY PAVER

Pewter

Pavestone Classic 80mm



Product Information	
Work Size (mm)	230 x 114 x 80
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	4.6
Approximate No. per m ²	37.1
No. Per Pack	210
Nominal Pack Weight (kg) ³	995
Breaking Load (kN) ¹	>12
Mean Abrasion Index (V _a) ²	<8
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Nil to Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Medium

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Pavestone Classic 80mm Masonry Paver Range













Charcoal

Donnybrook

Heritage Red

Limestone

Morocco

Pewter

Autumn Blend

Antique Blend

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

Autumn Blend

Pavestone Classic 80mm

Product Information	
Work Size (mm)	230 x 114 x 80
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	4.4
Approximate No. per m ²	37.1
No. Per Pack	210
Nominal Pack Weight (kg) ³	952
Breaking Load (kN) ¹	>10
Mean Abrasion Index (V _a) ²	<10
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Pavestone Classic 80mm Masonry Paver Range













Morocco

Pewter

Autumn Blend

Antique Blend

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

Antique Blend

Pavestone Classic 80mm

Product Information	
Work Size (mm)	230 x 114 x 80
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	4.6
Approximate No. per m ²	37.1
No. Per Pack	210
Nominal Pack Weight (kg) ³	995
Breaking Load (kN) ¹	>12
Mean Abrasion Index (V _a) ²	<7
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Pavestone Classic 80mm Masonry Paver Range













Charcoal Donny

Donnybrook Heritage Red

Limestone Morocco

Pewter

Autumn Blend

Antique Blend

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture