


MASONRY PAVER

Autumn Blend Promenade Classic 60mm





Product Information	
Work Size (mm)	300 x 300 x 60
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	12.0
Approximate No. per m ²	11.1
No. Per Pack	160
Nominal Pack Weight (kg) ³	1978
Breaking Load (kN) ¹	>12
Mean Abrasion Index (V _a) ²	<10
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Promenade Classic 60mm Masonry Paver Range



Morocco





Pewter











Other colours available on request



Heritage Red

Limestone

Steel Grey Note: If you require specific or improve product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days


³ Includes +3% for moisture



A BORAL COMPANY

MASONRY PAVER

Charcoal Promenade Classic 60mm





Product Information	
Work Size (mm)	300 x 300 x 60
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	11.7
Approximate No. per m ²	11.1
No. Per Pack	160
Nominal Pack Weight (kg) ³	1928
Breaking Load (kN) ¹	>12
Mean Abrasion Index (V _a) ²	<10
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight to Moderate
Liability to Lime Pitting	Nil
Solar Absorption Rating	Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Promenade Classic 60mm Masonry Paver Range



Autumn Blend


Morocco





Pewter





Steel Grey







Heritage Red

Other colours available on request

Limestone

Note: If you require specific or improve product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days


³ Includes +3% for moisture



A BORAL COMPANY

MASONRY PAVER

Donnybrook Promenade Classic 60mm





Product Information	
Work Size (mm)	300 x 300 x 60
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	11.7
Approximate No. per m ²	11.1
No. Per Pack	160
Nominal Pack Weight (kg) ³	1928
Breaking Load (kN) ¹	>12
Mean Abrasion Index (V _a) ²	<10
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Medium to Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

- ¹ At 28 days
- ² At 90 days
- ³ Includes +3% for moisture

Promenade Classic 60mm Masonry Paver Range



Autumn Blend

Morocco



Pewter





Steel Grey







Heritage Red

Other colours available on request




Limestone

Note: If you require specific or improve product specifications please contact your Sales Representative



MASONRY PAVER

Golden Sand Promenade Classic 60mm





Product Information	
Work Size (mm)	300 x 300 x 60
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	11.7
Approximate No. per m ²	11.1
No. Per Pack	160
Nominal Pack Weight (kg) ³	1928
Breaking Load (kN) ¹	>12
Mean Abrasion Index (V _a) ²	<10
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Light

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Morocco

Promenade Classic 60mm Masonry Paver Range



Note: If you require specific or improve product specifications please contact your Sales Representative

Pewter

DISCLAIMER. The information presented herein is supplied in good faith and to the best of our knowledge was correct at the time of preparation. No responsibility can be accepted by Midland Brick Company Pty Ltd, its staff or its agents for any errors or omissions. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, no responsibility can be accepted by Midland Brick Company Pty Ltd, its staff or its agents for any loss or damage caused by any person acting or refraining from action as a result of this information.

Other colours available on request

Steel Grey

¹ At 28 days


² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

Heritage Red Promenade Classic 60mm





Product Information	
Work Size (mm)	300 x 300 x 60
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	12.0
Approximate No. per m ²	11.1
No. Per Pack	160
Nominal Pack Weight (kg) ³	1978
Breaking Load (kN) ¹	>12
Mean Abrasion Index (V _a) ²	<10
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Promenade Classic 60mm Masonry Paver Range





Morocco



Pewter



Steel Grey







Other colours available on request

Note: If you require specific or improve product specifications please contact your Sales Representative

¹ At 28 days


² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

Limestone Promenade Classic 60mm





Limestone

Product Information	
Work Size (mm)	300 x 300 x 60
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	11.7
Approximate No. per m ²	11.1
No. Per Pack	160
Nominal Pack Weight (kg) ³	1928
Breaking Load (kN) ¹	>12
Mean Abrasion Index (V _a) ²	<10
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Nil to Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Light

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Promenade Classic 60mm Masonry Paver Range



Morocco Pewter Steel Grey Other colours available on request

Note: If you require specific or improve product specifications please contact your Sales Representative

¹ At 28 days


² At 90 days


³ Includes +3% for moisture



MASONRY PAVER

Morocco Promenade Classic 60mm





Product Information	
Work Size (mm)	300 x 300 x 60
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	11.7
Approximate No. per m²	11.1
No. Per Pack	160
Nominal Pack Weight (kg) ³	1928
Breaking Load (kN) ¹	>12
Mean Abrasion Index (V _a) ²	<10
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Morocco

Promenade Classic 60mm Masonry Paver Range



Note: If you require specific or improve product specifications please contact your Sales Representative

Pewter

DISCLAIMER. The information presented herein is supplied in good faith and to the best of our knowledge was correct at the time of preparation. No responsibility can be accepted by Midland Brick Company Pty Ltd, its staff or its agents for any errors or omissions. Users are advised to make their own determination as to the suitability of this information in relation to their particular purposes and specific circumstances. Since the information contained in this document may be applied under conditions beyond our control, no responsibility can be accepted by Midland Brick Company Pty Ltd, its staff or its agents for any loss or damage caused by any person acting or refraining from action as a result of this information.

Other colours available on request

¹ At 28 days


² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

Pewter Promenade Classic 60mm





Product Information	
Work Size (mm)	300 x 300 x 60
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	11.7
Approximate No. per m²	11.1
No. Per Pack	160
Nominal Pack Weight (kg) ³	1928
Breaking Load (kN) ¹	>12
Mean Abrasion Index (V _a) ²	<10
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Medium

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Promenade Classic 60mm Masonry Paver Range



Note: If you require specific or improve product specifications please contact your Sales Representative

¹ At 28 days


² At 90 days


³ Includes +3% for moisture



MASONRY PAVER

Steel Grey Promenade Classic 60mm





Product Information	
Work Size (mm)	300 x 300 x 60
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	11.7
Approximate No. per m ²	11.1
No. Per Pack	160
Nominal Pack Weight (kg) ³	1928
Breaking Load (kN) ¹	>12
Mean Abrasion Index (V _a) ²	<10
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Medium to Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

- ¹ At 28 days
- ² At 90 days
- ³ Includes +3% for moisture

Promenade Classic 60mm Masonry Paver Range



Note: If you require specific or improve product specifications please contact your Sales Representative