


A BORAL COMPANY

MASONRY PAVER

Amber Promenade Granite 40mm






Product Information	
Work Size (mm)	300 x 300 x 40
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	7.4
Approximate No. per m ²	11.1
No. Per Pack	224
Nominal Pack Weight (kg) ³	1707
Breaking Load (kN) ¹	>5
Mean Abrasion Index (V _a) ²	<10
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Medium

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Promenade Granite 40mm Masonry Paver Range



Titanium

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture




A BORAL COMPANY

MASONRY PAVER

Chalk

Promenade Granite 40mm





Product Information	
Work Size (mm)	300 x 300 x 40
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	7.4
Approximate No. per m ²	11.1
No. Per Pack	224
Nominal Pack Weight (kg) ³	1707
Breaking Load (kN) ¹	>5
Mean Abrasion Index (V _a) ²	<10
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Nil to Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Light

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Promenade Granite 40mm Masonry Paver Range



Chalk











Copper

Platinum

Rose Quartz

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture




A BORAL COMPANY

Rose Quartz

MASONRY PAVER

Copper Promenade Granite 40mm





Product Information	
Work Size (mm)	300 x 300 x 40
Dimensional Category	DPA2
CMAA Shape Category	Туре С
Approximate Dry Unit Weight (kg)	7.4
Approximate No. per m ²	11.1
No. Per Pack	224
Nominal Pack Weight (kg) ³	1707
Breaking Load (kN) ¹	>5
Mean Abrasion Index (V _a) ²	<10
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Promenade Granite 40mm Masonry Paver Range



anium Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days


² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

GraphitePromenade Granite 40mm






Product Information	
Work Size (mm)	300 x 300 x 40
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	7.4
Approximate No. per m²	11.1
No. Per Pack	224
Nominal Pack Weight (kg) ³	1707
Breaking Load (kN) ¹	>5
Mean Abrasion Index (V _a) ²	<10
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight to Moderate
Liability to Lime Pitting	Nil
Solar Absorption Rating	Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Promenade Granite 40mm Masonry Paver Range



Titanium

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days


² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

Platinum Promenade Granite 40mm





Product Information	
Work Size (mm)	300 x 300 x 40
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	7.4
Approximate No. per m ²	11.1
No. Per Pack	224
Nominal Pack Weight (kg) ³	1707
Breaking Load (kN) ¹	>5
Mean Abrasion Index (V _a) ²	<10
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Medium

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Promenade Granite 40mm Masonry Paver Range





Titanium

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days


² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

Rose Quartz Promenade Granite 40mm





Product Information	
Work Size (mm)	300 x 300 x 40
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	7.4
Approximate No. per m ²	11.1
No. Per Pack	224
Nominal Pack Weight (kg) ³	1707
Breaking Load (kN) ¹	>5
Mean Abrasion Index (V _a) ²	<10
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Dark


This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Promenade Granite 40mm Masonry Paver Range













DESCRIPTION OF THE PARTY OF THE

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days


² At 90 days

³ Includes +3% for moisture



MASONRY PAVER

TitaniumPromenade Granite 40mm





Product Information	
Work Size (mm)	300 x 300 x 40
Dimensional Category	DPA2
CMAA Shape Category	Type C
Approximate Dry Unit Weight (kg)	7.4
Approximate No. per m ²	11.1
No. Per Pack	224
Nominal Pack Weight (kg) ³	1707
Breaking Load (kN) ¹	>5
Mean Abrasion Index (V _a) ²	<10
Slip Resistance Category	P5
Cold Water Absorption (%)	<5
Coefficient of Contraction (mm/m)	<0.8
Durability Class	General Purpose
Potential to Effloresce	Slight
Liability to Lime Pitting	Nil
Solar Absorption Rating	Medium to Dark

This technical information represents average properties obtained from productions runs. If specific results are required, samples should be taken from current production runs. AS/NZS 4456 and 4586 are used as applicable. Durability classifications are based on product knowledge under local (Perth) climatic conditions. Colours are indicative only. Information subject to change without notice.

Promenade Granite 40mm Masonry Paver Range



Section 1982

Other colours available on request

Note: If you require specific or improved product specifications please contact your Sales Representative

¹ At 28 days

² At 90 days

³ Includes +3% for moisture